


ZIBO JINGGAN REFRACTORY IMPORT AND EXPORT CO.,LTD

Address:NO. 3, Yanhe Road, Boshan, Zibo, Shandong, China
Email:wp@cnjingganrefractory.com/sdwenping@163.com
Contact:Rose Tel/Wechat:+86-13275332819
Tel:86-533-4188518 Fax:86-533-4188518

Low Carbon Brown Corundum



1.Description:Low Carbon Brown Corundum is a high-grade refractory material, with less carbon residue, uniform and stable chemical composition, high density, low pulverization rate, high hardness and strong grinding force. The product is made of grinding grade bauxite by high temperature smelting at 2250 °C.

2.Specification ofLow Carbon Brown Corundum: 2-3000 mesh

3.Application: the product can be used to make all kinds of high-grade castables, gunning materials, ramming materials and other fire-resistant products. It can also be used to produce brown corundum brick, sliding plate brick, widely used in steel, cement, petrochemical, abrasive and other industries

4.Storage and transportation: waterproof and moisture-proof plastic bag packaging, convenient for transportation. Store in a dry environment.

5.Technical index

Specificatio n	Al2O3 %	Fe2O3 %	SiO2 %	TiO2 %	Color	Crysta l form	Hardness (mohs)	melt ing poin t ℃	True densit y g/cm3	magnet ic Materi al %	Service temperatur e
4#-80#	≥95	≤0.2	≤1.5	≤3.0	brown	Three square system	≥9	2050	≥3.90	≤0.05	1800

ZIBO JINGGAN REFRACTORY IMPORT AND EXPORT CO.,LTD

90#-150#	≥94	≤0.3	≤1.5	≤3.0	brown	Three square system	≥9	2050	≥3.90	≤0.05	1800
180#-220#	≥93.5	≤0.3	≤1.5	≤3.0	brown	Three square system	≥9	2050	≥3.90	≤0.05	1800

6. Good feedback of product use effect, the products have been exported to Australia, Oman, India.

7. We are a professional supplier, who can provide customers with free product technology, use and other issues.

Do you want to find a professional supplier of refractory products?

Do you want to find a professional supplier of graphite electrodes?

Do you want to find a stable and credible supplier?

Then let's contact with jinggan company

Contact me:

Email: wp@cnjingganrefractory.com / sdwenping@163.com

TEL: 86-0533-4188518 / FAX: 86-0533-4188518

Rose: +86-13275332819 (wechat/whatsapp number)